

III-P-1.17

NGHIÊN CỨU ĐIỀU CHẾ XÚC TÁC AG-VPO CHO PHẢN ỨNG OXY HÓA MỘT SỐ HỢP CHẤT HỮU CƠ

Cổ Thanh Thiện, Nguyễn Văn Kiên, Võ Xuân Nam

Khoa Hóa học, Trường ĐH KHTN, ĐHQG-HCM

Tóm tắt

Xúc tác vanadi phospho oxid (VPO) và xúc tác Ag-VPO đã được điều chế bằng nhiều phương pháp khác nhau với hiệu suất cao nhất đạt trên 93%. Từ hợp chất ban đầu là vanadi oxid (V_2O_5) được điều chế trong dung môi hữu cơ để tạo ra tiền chất là $VHPO_4 \cdot 0.5H_2O$, sau đó từ tiền chất này, kim loại bạc được gắn lên dưới cả hai dạng cơ bản là Ag và Ag^+ với thành phần thay đổi từ 0,5 ÷ 2.5%. Cả hai dạng xúc tác này được xác định tính chất hóa lý bằng nhiễu xạ tia X (XRD), kính hiển vi điện tử quét (SEM) và diện tích bề mặt (BET). Kết quả ban đầu cho thấy, diện tích bề mặt của mẫu bạc 1,5% có diện tích bề mặt cao nhất (40 m^2/g). Xúc tác này sau đó được khảo sát hoạt tính bằng phản ứng oxy hóa với chất nền là cyclohexan và toluen ở những điều kiện thời gian, nhiệt độ, nồng độ và dung môi khác nhau. Kết quả cho thấy xúc tác Ag-VPO có hoạt tính cao (> 98%) và độ chọn lọc tương đối tốt (> 80%). Đồng thời, khả năng thu hồi và tái sử dụng của xúc tác Ag-VPO cũng đã được khảo sát.

PREPARATION OF AG-VPO CATALYSTS AND THEIR APPLICATION TO HYDROCARBON OXIDATION

Abstract

Vanadium phosphorus oxides (VPO) and silver-promoted vanadyl pyrophosphate (Ag-VPO) catalysts were prepared by various methods in high yield (up to 93%). Starting from vanadium oxides, reaction were carried out by classical organic method to give the precursors $VHPO_4 \cdot 0.5H_2O$ after slightly drying overnight in air. The expected amount of silver nitrate was then added to the VPO precursors in alcohol and heated for 12 h to obtain Ag-VPO after calcinating 8 h. The synthesized catalysts were characterized by N_2 physisorption, X-ray diffraction, scanning electron microscopy. Interestingly, the 1.5%Ag-VPO give the best surface area of 40 m^2/g according to BET theory. The catalytic tests were performed in the oxidation of cyclohexane and toluene. The results showed that silver component significantly increased the overall activity (> 98%) and giving rise to good selectivity (> 80%). In addition, the used Ag-VPO catalysts were recycled for several times to confirm their stabilities.